



TK-SUPER SEAL PE™
Super Adhesion Sealant

Item No. TK-2204

PRODUCT DESCRIPTION

TK-SUPER SEAL PE™ is an elastic moisture curing sealant designed for use in metal architecture, curtain wall construction and joints subject to movement. SUPER SEAL PE™ adheres to difficult surfaces and permits its use on anodized metal and coatings such as Kynar 500® PVDF. SUPER SEAL PE™ will not stain absorbent stone substrates like limestone and marble. Its unique polyether chemistry eliminates out-gassing on green concrete and protects against “sun tanning” or discoloration when exposed to ultraviolet light.

SUPER SEAL PE™ is compatible with both the AIRMAX™ line of air/vapor/weather barriers and the CLIMATE TECH™ weather resistant barrier.

Features:

- Solvent-free, 100% solids will not shrink
- Non-slump, applies vertically and overhead
- 30 minute skin over
- No outgassing on damp surfaces
- Color stability, will not suntan
- Paintable within 24 hours
- +/- 50% joint movement

USES:

To fill and seal joints and seams in pre-cast concrete, block and masonry, curtain walls, expansion joints, exterior gypsum joints, cove joints, parapets, window and door frames, siding, and weather sealing.

SUPER SEAL PE™ is compatible with many construction materials such as: exterior gypsum, CMU, concrete, precast, block, brick, stone, masonry, Kynar 500® PVDF metal, aluminum and galvanized metal, wood, engineered plastics, PVC, glass, fiberglass and EPS foam.

APPLICATION PROCEDURES

PREPARATION:

Concrete Preparation:

Prior to application, remove any residual contamination by mechanical abrasion, sand blasting or power washing. On green concrete, remove all release agents, friable and loose concrete. Dry all visible and standing water prior to applying SUPER SEAL PE™. Install an appropriate backer rod to avoid three-point bonding.

Metal Preparation:

Prepare all metal to ensure maximum adhesion. Remove all rust, scale, and residue by wire brushing to a bright metal sheen. Remove films, loose or inappropriate coatings and oils with an appropriate solvent.

Wood Preparation:

Wood should be clean, sound and dry prior to sealant application. Allow treated wood to weather for six months prior to application. Remove all coatings and paint (or test for compatibility) to ensure proper bonding. Do not use on fire retardant lumber.

Joint Preparation:

Joint surfaces should be clean, dry and free from all contamination including dirt, oil, grease, tar, wax, rust and other substances that may inhibit the sealant's performance.

TECHNICAL DATA

Color:	Black
Gun Grade:	Zero slump
Viscosity:	750,000 cp +/- 150,000 cp
Density:	11.0 +/-0.2 lbs per gallon
Service Temperature(s):	-40°F to 200°F (-40°C to 93°C)
Tack Free Time (@ 70°F & 50% RH):	20-40 minutes
VOC Content:	< 19 g/l
A.I.M. Category:	This product is not currently regulated by 1999 Federal EPA VOC regulations

APPLICABLE STANDARDS

- ASTM C920, Type S, Grade NS, Class 50, Uses NT, T₂, M, G, A and O
- Federal Specification TT-S-00230-C Type II, Class A
- Corps of Engineers CRD-C-541, Type II, Class A
- Canadian Standards Board CAN 19, 13-M82
- SWR Institute Validated (Sealant Waterproofing and Restoration)
- AAMA 802.3-08 Type II, AAMA 803.3-08 Type I, and AAMA 805.2-08 Group C
- USDA Authorization for non-food contact

TESTING DATA

Elongation at Break:	700%
Peel Strength:	25-30 psi
Tensile Strength:	150-200 psi
Hardness Shore A:	20-23
Lap Shear Strength:	150-175 psi
Low temp. flexibility:	Pass -10°F (-23°C) 1/4" mandrel
Shrinkage:	No visible shrinkage after 14 days

Joint Design:

Install all joint applications per ASTM and SWRI recommendations and guidelines. Joints shall be designed with a depth to width ratio pf 1:2 (joint depth one-half the width).

Control the depth of the sealant by using a polyethylene backer rod that is 25% larger than the joint opening at standard temperature. To prevent three-point adhesion use a backer rod or bond breaker tape to ensure proper joint movement and a long lasting weatherproof seal. Where the joint configuration will not permit a backer rod,TK Products recommends that an alternative bond breaker be used.

Joint Width in Inches (mm)	Joint Depth in Inches (mm)
1/4 - 1/2 (6-13)	1/4 (6)
1/2 - 3/4 (13-19)	1/4 - 3/8 (6-10)
3/4 - 1 (19-25)	3/8 - 1/2 (10-13)
1 - 2 (25-50)	1/2 (13)

**TK Products recommends an appropriate substrate primer to be used on high moving joints or dissimilar substrates which require increased adhesion properties.*

APPLICATION:

Remove all dust, dirt, oil, loose paint, frost and other contamination from all working surfaces with alcohol. DO NOT USE petroleum solvents such as mineral spirits or xylene. Maintain SUPER SEAL PE™ at room temperature before applying to ensure easy gunning and tooling. Test and evaluate to ensure adequate adhesion. Carefully gun the sealant with a smooth, continuous bead. If tooling is needed, do so within fifteen minutes of application.

For gypsum sheathing seam applications, a crown bead nozzle applicator tip should be used. Apply SUPER SEAL PE™ to a depth of 1/4", or an 80-100 mil crown bead. Continue bead past joint seam 1/4" onto gypsum sheathing, making certain that material is equal on both sides of the joint. To promote proper adhesion, "knock" the material to disperse bead into the joint.

CLEAN-UP:

Wet sealant may be removed using a solvent such as alcohol. If cured, SUPER SEAL PE™ may be removed by abrading or scraping the substrate.

STORAGE:

Store original, unopened containers in a cool, dry area. Protect unopened containers from water, heat and direct sunlight. Elevated temperatures will reduce shelf life. SUPER SEAL PE™ will not freeze.

SHELF LIFE:

Shelf life is 12 months from manufactured date when stored at 70°F (21°C) with 50% relative humidity. High temperatures and high relative humidity may significantly reduce shelf life.

LIMITATIONS:

- In areas where prolonged chemical exposure is anticipated, contact technical services for recommendations.
- Allow product to achieve surface cure before applying fluid applied air barriers. Cure times may be greatly prolonged by cold weather and/ or low relative humidity. If this product is not allowed to adequately surface cure, the fluid applied air barrier may run and fail to adhere. If air barrier fails to adhere, allow SUPER SEAL PE™ to adequately cure then reapply air barrier.
- Allow treated wood to "cure" for six months prior to application per APA guidelines.
- Do not use in areas subject to continuous immersion.
- Do not store in elevated temperatures.
- Remove all coatings and sealers before application.
- Contact customer service for application guidelines where temperatures are below 32°F (0°C).
- Test and evaluate all paints before application. Polyurethane and oil based paints may dry slowly.
- Do not use on TPO without primer.

FIRST AID:

- Consult this product's safety data sheet for additional health and safety information. Safety Data Sheets are available through TK distributors, the TK office and the TK website.

AVAILABILITY:

TK-SUPER SEAL PE™ is available through TK Distributors. Contact TK Products for the nearest distributor. Packaged in 2-gallon pails and 20 oz (600 ml) cartridges.

FOR PROFESSIONAL USE ONLY

03/17 Last Rev. 05/16

CONDITIONS OF SALE/ LIMITED WARRANTY

TK Products, division of the Sierra Corporation, warrants that its products conform to the label descriptions, are free from manufacturing defects, and are fit for the ordinary purposes for which such goods are used. Inasmuch as the use of TK Products' product by others and other factors affecting product performance are beyond TK Products' control, TK Products does not guarantee the results to be obtained. There are no warranties except as stated herein, either express or implied, including implied warranties of merchantability or fitness for a particular purpose. **SHOULD ANY TK PRODUCTS' PRODUCT FAIL TO GIVE SATISFACTORY RESULTS, TK PRODUCTS WILL REPLACE THE PRODUCT, OR AT ITS OPTION, REFUND THE PURCHASE PRICE. THIS IS THE SOLE AND EXCLUSIVE REMEDY FOR ANY FAILURE OF TK PRODUCTS' PRODUCTS TO PERFORM AS WARRANTED AND SHALL ALSO CONSTITUTE LIQUIDATED DAMAGES IN CASE OF LOSS. UNDER NO CIRCUMSTANCES SHALL THE BUYER BE ENTITLED TO ANY OTHER REMEDY OR DAMAGES. REMEDIES FOR INCIDENTAL AND CONSEQUENTIAL DAMAGES ARE SPECIFICALLY EXCLUDED. TK Products does not authorize any person to assume for it any other liability in connection with the sale or use of its products unless specifically authorized by TK Products in writing.**

TK DISCLAIMER:

Every effort has been made to ensure the accuracy of the above information and to avoid infringement of any patent or copyright. The information is based on field tests by government and private agencies, as well as lab tests, and on technical data from raw material manufacturers. The person(s) specifying or requesting the use of these products is responsible for assuring their suitability for a specific use, as well as the proper application of the products. Where there is any question as to the suitability of a particular product, a small test patch is recommended. See also CONDITIONS OF SALE/ LIMITED WARRANTY (Section 7) above.

