



ISO 9001 CERTIFIED

DC WB DISSIPATING CURE 2519

Water Based Dissipating Curing Compound

Item No. TK-2519 DC WB (clear); TK-2519 DC WB/TK-RED DYE WB (translucent red)

PRODUCT DESCRIPTION

DC WB DISSIPATING CURE 2519 is a 100% hydrocarbon resin, water base curing compound for fresh concrete. Designed to adhere to freshly placed concrete and enhance its overall strength, TK-2519 DC WB provides excellent curing properties and moisture retention for maximum surface density and hardness. Over time, DC WB DISSIPATING CURE 2519 naturally wears away from the surface to prepare concrete for coating with a multitude of protective and/or decorative topcoats and treatments. Available in clear, or translucent red with a fugitive dye additive.

Features:

- Controls moisture loss and aids in complete hydration of the cement during the curing process.
- Results in surfaces with maximum hardness and density.
- Becomes brittle within weeks of application (typically < 8 weeks under normal traffic conditions) and naturally deteriorates from the surface to leave it prepared for subsequent concrete coatings and treatments.

USES:

Suitable for exterior use on any freshly placed concrete surface where superior curing qualities are desired.

May also be used on interior surfaces, however, mechanical means may be required in order for the product to dissipate in a timely manner when used indoors.

APPLICATION PROCEDURES:

MIXING:

The material must be mixed prior to use. Do not thin with solvents as it is unlawful to further reduce with non-exempt solvents.

Mixing with Fugitive Dye Additive:

A) Mix (1) gallon TK-RED DYE WB to (1) 55-gallon drum DC WB DISSIPATING CURE 2519.

B) Mix (1) short filled pint TK-RED DYE WB to (1) 5-gallon pail DC WB DISSIPATING CURE 2519.

APPLICATION:

DC WB DISSIPATING CURE 2519 may be applied by sprayer, brush or roller. Do not over-apply as this will inhibit dissipation and will make the product difficult to manually remove. Ambient and substrate temperatures must be at least 40°F and remain above 40°F throughout the entire cure time of the coating.

DC WB DISSIPATING CURE 2519 is also available with a red dye additive to aid in uniform application and ease of inspection following application. See mixing instructions above.

TECHNICAL DATA

Composition and Materials:	Hydrocarbon resin in a solvent/ water emulsion
VOC Content:	< 350 g/l
A.I.M. Category:	Concrete Curing Compound Maximum VOC 350 g/l
Specification:	ASTM C309 Type 1, Class A, B and Type 1D with a red dye added.

TESTING DATA

Applicable Standard	ASTM Requirement	Product Performance
ASTM C156: Water Retention	< 0.55 kg/m ²	0.35 kg/m ² @ 200 ft ² /gallon
ASTM C309 (10.3): Drying Time	< 4 hours	13 minutes
ASTM D1309: Long Term Settling Test	> 3 rating	10 rating
ASTM D2369: Solids	NA	18.8%

CLEAN UP:

Clean tools, equipment and spills with soap and water before the material dries.

COVERAGE:

Surface	Coverage
Broomed finishes	200-400 sq.ft./gal
Troweled finishes	
Exterior	300 sq.ft./gal
Interior	400 sq.ft./gal

Coverage rates are provided as a guideline only. Many factors including surface texture, porosity and weather conditions will determine actual coverage rates.

MAINTENANCE:

On interior surfaces and in areas of light traffic, a power sweeper with stiff bristle brushes, or a buffer with a coarse 3M® pad may be used to remove DC WB DISSIPATING CURE 2519 from the surface. A hard brooming and/or washing should precede any further activity.

LIMITATIONS:

- Over application of this product will inhibit dissipation and will make it difficult to manually remove.
- Keep from freezing.
- As a resin based curing compound, DC WB DISSIPATING CURE 2519 is not intended as a protective sealing membrane for concrete surfaces.
- Do not apply when ambient or substrate temperature is below 40°F or is expected to fall below 40°F within the cure time of the coating.

FIRST AID:

- Consult this product's safety data sheet for additional health and safety information. Safety Data Sheets are available through TK distributors, the TK office and the TK website.

AVAILABILITY:

DC WB DISSIPATING CURE 2519 is available through TK Distributors. Contact TK Products for the nearest distributor.

Packaged in 55-gallon drums and 5-gallon pails.

FOR PROFESSIONAL USE ONLY

01/18 Last Rev. 10/17

CONDITIONS OF SALE/ LIMITED WARRANTY

TK Products, division of the Sierra Corporation, warrants that its products conform to the label descriptions, are free from manufacturing defects, and are fit for the ordinary purposes for which such goods are used. Inasmuch as the use of TK Products' product by others and other factors affecting product performance are beyond TK Products' control, TK Products does not guarantee the results to be obtained. There are no warranties except as stated herein, either express or implied, including implied warranties of merchantability or fitness for a particular purpose. SHOULD ANY TK PRODUCTS' PRODUCT FAIL TO GIVE SATISFACTORY RESULTS, TK PRODUCTS WILL REPLACE THE PRODUCT, OR AT ITS OPTION, REFUND THE PURCHASE PRICE. THIS IS THE SOLE AND EXCLUSIVE REMEDY FOR ANY FAILURE OF TK PRODUCTS' PRODUCTS TO PERFORM AS WARRANTED AND SHALL ALSO CONSTITUTE LIQUIDATED DAMAGES IN CASE OF LOSS. UNDER NO CIRCUMSTANCES SHALL THE BUYER BE ENTITLED TO ANY OTHER REMEDY OR DAMAGES. REMEDIES FOR INCIDENTAL AND CONSEQUENTIAL DAMAGES ARE SPECIFICALLY EXCLUDED. TK Products does not authorize any person to assume for it any other liability in connection with the sale or use of its products unless specifically authorized by TK Products in writing.

TK DISCLAIMER:

Every effort has been made to ensure the accuracy of the above information and to avoid infringement of any patent or copyright. The information is based on field tests by government and private agencies, as well as lab tests, and on technical data from raw material manufacturers. The person(s) specifying or requesting the use of these products is responsible for assuring their suitability for a specific use, as well as the proper application of the products. Where there is any question as to the suitability of a particular product, a small test patch is recommended. See also CONDITIONS OF SALE/ LIMITED WARRANTY (Section 7) above.

**TK Products Construction Coatings**

11400 West 47th Street Minnetonka, MN 55343

800-441-2129 toll free | 952-938-8084 fax | www.tkproducts.com