



TK-2415 HMWMA BRIDGE DECK SEALER

High Molecular Weight Methacrylate Coating

Item No. TK-2415

PRODUCT DESCRIPTION

TK-2415 HMWMA BRIDGE DECK SEALER is a fast curing, 100% solids, completely reactive polymer system designed to deeply and rapidly penetrate into cracks and pores in concrete surfaces. TK-2415 HMWMA BRIDGE DECK SEALER re-bonds cracks and acts as a tenacious barrier to protect high traffic surfaces from water and environmental contamination.

Features:

- Provides resistance from water and chloride ion penetration
- Resists effects of weathering and aging
- Usable in a wide range of substrate temperatures (from 50°F to 90°F), allowing for an extended application season
- Fast curing - permits surface reopening in minimal time (in daytime, sunlight conditions)
- Low viscosity and surface tension result in excellent penetration into cracks
- Low odor, low VOC content
- User friendly and easy to use
- High flash point (less flammable)

USES:

Suitable for exterior application to horizontal concrete surfaces, bridge decks and parking structures.

APPLICATION PROCEDURES:

PREPARATION:

TK-2415 HMWMA BRIDGE DECK SEALER requires minimal surface preparation, however the surface must be clean, dry and free of dirt, dust, oil, wax, curing compounds, efflorescence, laitance and any other bond-breaking materials. Concrete and bridge decks that are reasonably clean may be swept with high-pressure air to remove small amounts of dirt. If wet preparation methods are used, the surface must be adequately dry before application.

MIXING:

TK-2415 HMWMA BRIDGE DECK SEALER is a three-component product and should be mixed using the following starting point formulas:

MIXING CHART

Substrate Temperature (°F)	TK-2415 Sealer (component "A")	Accelerator (component "B")	CHP Catalyst (component "C")
90°F	4 gallons	0.65 fl. oz.	7.3 fl. oz. (1 unit)
80°F	4 gallons	1.3 fl. oz.	7.3 fl. oz. (1 unit)
70°F	4 gallons	2.6 fl. oz.	7.3 fl. oz. (1 unit)
60°F	4 gallons	3.9 fl. oz.	7.3 fl. oz. (1 unit)
50°F	4 gallons	5.2 fl. oz.	7.3 fl. oz. (1 unit)

Note: Modifications may be required when applying in significantly hotter/cooler conditions or during nighttime applications. When substrate temperatures are consistently above 90°F, night time application is recommended. Otherwise, reducing the amount of Accelerator (component "B") should be considered in hotter temperature applications.

TECHNICAL DATA

Color:	Clear
Flash Point:	> 200°F
Specific Gravity:	1.03
VOC Content:	0 g/l
A.I.M. Category:	Waterproofing Sealers, Concrete/Masonry Maximum VOC 400 g/l

TESTING DATA

TEST	RESULTS
Viscosity (ASTM D2196):	< 25 cps
Bond Strength (ASTM C882, Slant Shear):	2300 psi
Tensile Strength (ASTM D638):	4368 psi
Tensile Elongation (ASTM D638):	1.7%
Compressive Strength (ASTM D695):	8960 psi
Gel Time (ASTM D2471):	17 minutes
Tack Free Time (ASTM D1640):	< 5 hours

Mixing Instructions:

Begin by combining the CHP Catalyst (component "C") directly into the TK-2415 Sealer (component "A") using a variable speed drill motor mixer. Remove container lid and mechanically mix in any material that is floating on the surface. Any material that has adhered to the lid should be scraped off and added to this mixture. Finally, add the appropriate amount of Accelerator (component "B") and mix thoroughly.

Special Mixing Notes:

- Component "C" is supplied in pre-measured units for use with either 4-gallon or 50-gallon kits.
- Component "B" is supplied in a fully filled quart bottle. The applicator must measure the appropriate amount of Component "B" for the substrate temperature and size of kit being used (see Mixing Chart for guidelines).

WARNING! Do not allow the Accelerator (component "B") to come into direct contact with the CHP Catalyst (component "C") as this could result in an exothermic mixture. Keep mixing containers separate and do not cross contaminate.

It is important to follow the mixing instructions above and to take precautions by wearing personal protection equipment. Before using this product, thoroughly read and understand this product's label, technical data sheet and Safety Data Sheet (SDS). Eye protection should always be worn when working with hazardous materials. If splashing is possible, a full face shield is advised. Eye rinse stations should be readily available at the job site. Avoid contact with the skin by wearing protective gloves, footwear and aprons if the possibility of splashing on clothing exists. If material gets onto clothing, immediately remove clothing and wash affected area with soap and water. Respirator use may be required in the event of poor ventilation or if the victim is experiencing effects from vapor exposure.

APPLICATION:

Upon mixing, the material should be applied immediately as working time is 15-30 minutes before the product begins to gel. Dumping and spreading of the material onto a cooler surface will extend this time.

TK-2415 HMWMA BRIDGE DECK SEALER is to be applied as a flood coat and in a gravity fed process by broom, roller or squeegee. Do not allow material to pond on the surface. The typical coverage rate is 60-120 square feet per gallon. Some areas may absorb greater amounts of TK-2415 HMWMA BRIDGE DECK SEALER, resulting in dry spots.

These areas should be treated with additional amounts of product until it is absorbed to the point of refusal. On very porous surfaces, a second treatment may be required.

For added traction and skid resistance, TK Products recommends the use of 30 mesh aggregate (dry) to be broadcast at a rate of approximately 4-lbs./100 square feet into the resin before it has cured. Aggregate may be broadcast by hand throwing or by spreader. Excessive loose aggregate must be removed before reopening the surface to traffic.

DRYING TIME:

Note that air and substrate temperatures, humidity levels and exposure to UV light can all have a significant effect on drying times. Due to these variations, a test patch should be applied using the application procedures intended for the project and the area evaluated to determine the particular catalyst ratios required.

CLEAN UP:

Clean tools and spills with Xylene before the material cures.

COVERAGE:

Typical coverage rate is between 60-120 square feet per gallon. Highly porous surfaces will result in reduced coverage rates.

Coverage rates are provided as a guideline only. Many factors including surface texture, porosity and weather conditions will determine actual coverage rates.

LIMITATIONS:

- Do not thin as the addition of solvents will prevent proper curing.
- Substrate temperatures should be 50°F and rising during application. Colder temperatures will increase dry times.
- The product is fast curing during optimal daytime, sunlight conditions. Modifications may be necessary in order to apply this product at night or in extreme temperatures.

STORAGE:

TK-2415 HMWMA BRIDGE DECK SEALER should be stored in a cool, dry place out of direct sunlight. Shelf life is 6-9 months in original, unopened containers.

FIRST AID:

- Consult this product's safety data sheet for additional health and safety information. Safety Data Sheets are available through TK distributors, the TK office and the TK website.
- Contact with eyes may cause irritation including burning, watering and redness. If the material gets in the eyes, flush with large amounts of water for 15 minutes, lifting upper and lower eyelids. If irritation persists, seek medical attention.
- Contact with skin may cause mild irritation including redness, burning and drying and cracking of the skin. Continued exposure may develop into dermatitis. May cause irritation with redness, pain and skin sensitization in some individuals. If the material comes into contact with the skin, wash contaminated area with soap and water. Remove and launder contaminated clothing.
- Inhalation of vapors and mists may cause irritation of the nose, throat and lungs and may lead to headaches and nausea. In the event of over-exposure to vapors, relocate victim to fresh air and provide oxygen if breathing is difficult. If breathing has stopped, administer artificial respiration and seek medical attention if conditions persist.

AVAILABILITY:

TK-2415 HMWMA BRIDGE DECK SEALER is available through TK Distributors. Contact TK Products for the nearest distributor.

Packaged in 55-gallon and 5-gallon kits.

FOR PROFESSIONAL USE ONLY

08/16 Last Rev. 06/16

CONDITIONS OF SALE/ LIMITED WARRANTY

TK Products, division of the Sierra Corporation, warrants that its products conform to the label descriptions, are free from manufacturing defects, and are fit for the ordinary purposes for which such goods are used. Inasmuch as the use of TK Products' product by others and other factors affecting product performance are beyond TK Products' control, TK Products does not guarantee the results to be obtained. There are no warranties except as stated herein, either express or implied, including implied warranties of merchantability or fitness for a particular purpose. **SHOULD ANY TK PRODUCTS' PRODUCT FAIL TO GIVE SATISFACTORY RESULTS, TK PRODUCTS WILL REPLACE THE PRODUCT, OR AT ITS OPTION, REFUND THE PURCHASE PRICE. THIS IS THE SOLE AND EXCLUSIVE REMEDY FOR ANY FAILURE OF TK PRODUCTS' PRODUCTS TO PERFORM AS WARRANTED AND SHALL ALSO CONSTITUTE LIQUIDATED DAMAGES IN CASE OF LOSS. UNDER NO CIRCUMSTANCES SHALL THE BUYER BE ENTITLED TO ANY OTHER REMEDY OR DAMAGES. REMEDIES FOR INCIDENTAL AND CONSEQUENTIAL DAMAGES ARE SPECIFICALLY EXCLUDED.** TK Products does not authorize any person to assume for it any other liability in connection with the sale or use of its products unless specifically authorized by TK Products in writing.

TK DISCLAIMER:

Every effort has been made to ensure the accuracy of the above information and to avoid infringement of any patent or copyright. The information is based on field tests by government and private agencies, as well as lab tests, and on technical data from raw material manufacturers. The person(s) specifying or requesting the use of these products is responsible for assuring their suitability for a specific use, as well as the proper application of the products. Where there is any question as to the suitability of a particular product, a small test patch is recommended. See also CONDITIONS OF SALE/ LIMITED WARRANTY above.