



TK-290 WB

Water Borne Deep Penetrating Water Repellent

Item No. TK-290 WB

PRODUCT DESCRIPTION

TK-290 WB is a water-borne silane/siloxane concrete and masonry water repellent to prevent water damage by eliminating moisture present on the surface. TK-290WB penetrates up to 1/4" and chemically bonds with the substrate to become a permanent part of the concrete, prohibiting water and chloride ion intrusion that could cause surface deterioration.

Features:

- Very low VOC's (Volatile Organic Compounds).
- Forms a chemical, and permanent, bond with the substrate to provide ultimate protection against damage due to water and deicing chemical intrusion, acid rain, freeze/thaw exposure, airborne dirt, smog, industrial fumes and most other atmospheric chemicals.
- Penetrates up to 1/4" and eliminates surface moisture which can lead to spalling, freeze damage and rebar corrosion.
- Outperforms typical water repellents which can only bond physically with the surface and thus provide marginal protection.
- The coating is colorless, non-staining and non-yellowing.

USES:

Suitable for above-grade exterior surfaces, vertical or horizontal. Use to protect any concrete, burnish block, CMU, single wythe, masonry or cementitious surface. Applications include parking structures, bridge decks and ramps, piers and pilings, precast concrete, poured concrete walls, natural and synthetic stone, burnish block, split face block, stucco and clay brick.

*This product is not suitable for use on gypsum, glazed brick or block which will be painted over.

APPLICATION PROCEDURES:

PREPARATION:

Before using this product, read the Safety Data Sheet for complete safety information.

All surfaces to be treated must be clean and structurally sound. Thoroughly clean surfaces to remove all grease, oils, form oils or other contaminants. TK-290WB should be applied to dry surfaces only. It is recommended that surface temperatures be 40°F or above at the time of application to ensure that surfaces are frost-free.

Existing Concrete preparation - Unsound concrete should be removed and cracks or deteriorated areas repaired prior to application. Surfaces may need to be mechanically abraded to achieve maximum penetration.

New Concrete preparation - Water cure fresh concrete or use TK-DC WB DISSIPATING CURING COMPOUND 2519*. As a standard procedure, fresh concrete should be allowed to cure for 28 days before applying waterproofing treatments. The product may be applied sooner under prescribed conditions and procedures specified by TK Products.

A test patch should always be performed to determine proper results and coverage rates prior to application.

MIXING:

The material is ready for use and requires no mixing. Do not thin or dilute.

APPLICATION:

Apply by roller or spray equipment in a uniform manner and in sufficient quantity to completely wet out the substrate with a minimum of 2" run down. Avoid puddling on horizontal surfaces. Very porous surfaces may require two coats.

Decorative Block application - When applying to decorative block or substrates where darkening of the surface is undesirable, fully saturate the surface with no rundown.

continued on next page...

TECHNICAL DATA

Composition and Materials:	A water borne, silane/siloxane water repellent.
Density:	6.72 lbs
Flash Point:	40°F
VOC Content**:	< 120 g/l
A.I.M. Category:	Low Solids Coating Maximum VOC 120 g/l
Applicable Standards:	- ASTM C666 Resistance of Concrete to Rapid Freezing and Thawing - ASTM C672 Scaling Resistance - NCHRP 244 (water absorption, % water vapor transmission and % reduction in chloride intrusion)

TYPICAL PROPERTIES

TK-290 WB is characterized by the following properties:

- Excellent penetration
- High alkali resistance and suitability for either alkaline or neutral substrates
- Low volatility
- Dries tack free
- Provides early water repellency
- Exhibits droplet effect

CLEAN UP:

Clean tools, equipment and spills with soap and water before the material dries.

COVERAGE:

The recommended coverage rate for most concrete substrates is 125 square feet per gallon. Very porous surfaces may require two coats.

Surface	Coverage
Bridge decks/ramps	100-200 square feet/gallon
Smooth concrete	150-250 square feet/gallon
Exposed aggregate:	100-200 square feet/gallon
Concrete block:	40-100 square feet/gallon

Coverage rates are provided as a guideline only. Many factors including surface texture, porosity and weather conditions will determine actual coverage rates.

MAINTENANCE:

If wear patterns occur, TK-290 WB may be reapplied to affected areas.

LIMITATIONS:

- KEEP FROM FREEZING.
- Do not use below-grade or under hydrostatic pressure.
- Do not apply if rain is expected within 4-6 hours of application.
- Over application may cause darkening or discoloration of the surface.
- Application to inappropriate or non-compatible substrates may affect adhesion of subsequent coatings.
- Use with adequate ventilation.
- May leave a waxy coating if over-applied or applied over sealed surfaces.
- Not suitable for use on gypsum.

PROTECTION OF VEGETATION, GLASS AND ALUMINUM SURFACES:

Avoid contact with live vegetation, glass and aluminum. If properly protecting these surfaces is impractical, the following steps should be performed:

- 1) Minimize contact of TK-290 WB with live vegetation, glass and aluminum surfaces.
- 2) If TK-290 WB comes into contact with glass or aluminum, thoroughly clean surfaces with Windex® or an ammonia cleaner while the material is still wet.

FIRST AID:

- Consult this product's safety data sheet for additional health and safety information. Safety Data Sheets are available through TK distributors, the TK office and the TK website.

AVAILABILITY:

TK-290 WB is available through TK Distributors. Contact TK Products for the nearest distributor.

Packaged in 55-gallon drums, 5-gallon pails and 1-gallon cans.

FOR PROFESSIONAL USE ONLY

NOTES:

*TK-DC WB DISSIPATING CURING COMPOUND 2519 must be purchased separately

09/16 Last Rev. 04/15

CONDITIONS OF SALE/ LIMITED WARRANTY

TK Products, division of the Sierra Corporation, warrants that its products conform to the label descriptions, are free from manufacturing defects, and are fit for the ordinary purposes for which such goods are used. Inasmuch as the use of TK Products' product by others and other factors affecting product performance are beyond TK Products' control, TK Products does not guarantee the results to be obtained. There are no warranties except as stated herein, either express or implied, including implied warranties of merchantability or fitness for a particular purpose. **SHOULD ANY TK PRODUCTS' PRODUCT FAIL TO GIVE SATISFACTORY RESULTS, TK PRODUCTS WILL REPLACE THE PRODUCT, OR AT ITS OPTION, REFUND THE PURCHASE PRICE. THIS IS THE SOLE AND EXCLUSIVE REMEDY FOR ANY FAILURE OF TK PRODUCTS' PRODUCTS TO PERFORM AS WARRANTED AND SHALL ALSO CONSTITUTE LIQUIDATED DAMAGES IN CASE OF LOSS. UNDER NO CIRCUMSTANCES SHALL THE BUYER BE ENTITLED TO ANY OTHER REMEDY OR DAMAGES. REMEDIES FOR INCIDENTAL AND CONSEQUENTIAL DAMAGES ARE SPECIFICALLY EXCLUDED.** TK Products does not authorize any person to assume for it any other liability in connection with the sale or use of its products unless specifically authorized by TK Products in writing.

TK DISCLAIMER:

Every effort has been made to ensure the accuracy of the above information and to avoid infringement of any patent or copyright. The information is based on field tests by government and private agencies, as well as lab tests, and on technical data from raw material manufacturers. The person(s) specifying or requesting the use of these products is responsible for assuring their suitability for a specific use, as well as the proper application of the products. Where there is any question as to the suitability of a particular product, a small test patch is recommended. See also CONDITIONS OF SALE/ LIMITED WARRANTY (Section 7) above.