

TK-HYDROMAX® 2002

Foundation Waterproof Coating (Commercial)

Solvent Base | IAPMO ER# 0338 | Division 7: Section 071416 - Cold Fluid Applied Waterproofing

Item No. TK-2002

PRODUCT DESCRIPTION

TK-HYDROMAX® 2002 is a non-breathable, single component, fluid applied foundation coating. This solvent-based, rubberized polymer formulation is used to waterproof below-grade concrete surfaces.

USES:

Suitable for exterior use on below-grade foundation walls, CMU and poured concrete.

APPLICATION PROCEDURES:

PREPARATION:

A clean, dry and frost free surface is required. Any dirt, oils, grease, debris, concrete laitance or other contaminants must be removed. Surfaces should be smooth and free of any voids, spalled areas, loose substrate, protrusions or coarse aggregate. To remove dirt, dust or loose stones, the substrate must be wire-brushed, swept with a stiff broom or blown with high pressure air. Surfaces of poor quality or with excessive laitance may require shotblasting or pressure washing to rid it of contaminants and to provide a dense, smooth surface. Defects such as spalled concrete or poorly joined areas must be repaired. Any and all previous coatings must be removed prior to application of this product. All masonry joints must be tooled and brushed. The assembly wall is to be unparge.

When applying to CMU substrates, make sure all mortar joints are tooled both inside and outside to form a continuous mortar joint.

When applying to poured concrete, remove all form ties inside and out, while pre-treating all tie holes with TK-Super Seal, or pre-approved caulk prior to the waterproofing application.

New/"Green" Concrete and Damp Surface preparation

New concrete should be allowed to cure until the surface appears dry. For proper adhesion, any concrete walls or concrete blocks that have been placed late in the year should be allowed to gain sufficient strength prior to application. TK-HYDROMAX® 2002 may be applied to "green" concrete, however any visible, running or standing water should be removed prior to application. Control joints should be sprayed using TK-HYDROMAX® 2002. Once cured, apply TK-CLIMATE FLASH™ sheet membrane, or an approved equal, and extend 6" on both sides of joint. Caulk edges with TK-SUPER SEAL™.

Existing Concrete preparation

Tie-holes, bug holes and surface abnormalities exceeding 1/2" in diameter or 1/8" deep (or both) shall be pretreated using either a small amount of TK-HYDROMAX® 2002 back rolled, or a lean concrete mix of grout. Surfaces that are cracked, pitted, honeycombed or heavily bugholed may be filled by spraying with TK-HYDROMAX® 2002 and back rolled to ensure the product is pushed to all edges of the voids. Immediately apply a full coat of TK-HYDROMAX® 2002 at specified amounts. Utilizing this method, however will consume a higher amount of material,

TECHNICAL DATA	
Composition and Materials:	A rubberized polymer blend in an aromatic hydrocarbon blend solvent.
% Solids by Weight:	48-50%
Flash Point:	Flammable, less than 100°F
Drying Time:	1 hour (recoat 2-4 hours) 3-7 days
VOC Content:	< 600 g/l
A.I.M. Category:	Waterproofing Sealers and Treatments Maximum VOC 600 g/l

TESTING DATA	
APPLICABLE STANDARDS	TK-HYDROMAX® 2002 PERFORMANCE
ASTM C 1306/D5385: Hydrostatic Pressure over Cracks	.310 (45.0) MPa (psig)
ASTM C 836-03 Section 6.10: Adhesion Strength	11.9 lbf/inch
ASTM D 2939: Resistance to Water	Passed
ASTM C 836-89 Section 6.7: Low Temperature Flexibility and Crack Bridging	11.9 lbf/inch
ASTM D 412: Vulcanized Rubber and Thermoplastic Elastomers - Tension	637%
ASTM E 96-00: Water Vapor Transmission and Vapor Permeability Test, Procedure B	0.05 Perms 0.0015 Permeability
ASTM C 1305: Crack Bridging Ability	Pass, showed no cracking or loss of adhesion upon completion of 10 cycles of movement at -15°F.
ASTM C 1306: Hydrostatic Pressure Resistance	Passed long-term test
ASTM C 1522: Extensibility after Heat Aging	No cracks, tears or holes observed after extending the membrane.

therefore it may be more efficient to fill surface deficiencies with a parge coat of lean mortar mix prior to application of this product. Gaps may also be filled with a compatible sealant or caulk. Remove windows, protrusions and form match lines. High spots greater than 1/32" in height should also be removed.

Drain and Penetration Detailing - Once the waterproofing membrane has cured, any penetration openings must be sealed and stabilized.

Back Fill and Drain Tile - Install a fabric socked drain tile with proper hook up and daylight. Back fill with clean pea stone for proper drainage.

MIXING:

The material is ready for use and requires no mixing unless signs of separation are evident. It is unlawful to further reduce with non-exempt solvents.

APPLICATION:

TK-HYDROMAX® 2002 should be applied directly to concrete by spray. A typical sprayer is a Graco 733/833 45:1 airless with a 0.039 tip. Brush and/or roller will work for application to smaller areas or for touch ups.

Application of Drainage, Protection or Insulation - Protect TK-HYDROMAX® 2002 from other traffic, construction materials or backfill to avoid damaging it. Once the membrane has properly cured, use a protection/drainage composite with filter fabric. Extruded polystyrene insulation boards are compatible with TK-HYDROMAX® 2002 once the product has fully cured.

CLEAN UP:

Use TK-00 XYLENE to clean tools and equipment. Pump solvent through the spray equipment to remove material residue which can clog the hose and wand assembly.

COVERAGE:

The coverage rate is inversely affected by the texture and porosity of the substrate. One coat is sufficiently applied at 30-32 square feet per gallon (50 wet mils). Inspect the surface and make certain that the coverage of the coating is continuous and uninterrupted. Any area that is thin may be recoated.

Coverage rates are provided as a guideline only. Many factors including surface texture, porosity and weather conditions will determine actual coverage rates.

MAINTENANCE:

Minimal maintenance is required. If weathering occurs, TK-HYDROMAX® 2002 may be reapplied to the affected area.

LIMITATIONS:

- SAFETY PRECAUTIONS: A fitted organic/carbon filter respirator, and appropriate eye protection, must be worn at all times during application of this product. The coating must be applied at temperatures between 0°F to 100°F.
- Apply directly to structural surfaces.
- Do not apply over lightweight insulating concrete forms. If insulation is used it must be installed overtop the membrane.

FIRST AID:

- Consult this product's safety data sheet for additional health and safety information. Safety Data Sheets are available through TK distributors, the TK office and the TK website.

AVAILABILITY:

TK-HYDROMAX® 2002 is available through TK Distributors. Contact TK Products for the nearest distributor.

Available in Dawn Mist and Stone Gray.

Available in residential and commercial formulations.

Packaged in 55-gallon drums and 5-gallon pails.

FOR PROFESSIONAL USE ONLY

04/17 Last Rev. 01/16

CONDITIONS OF SALE/ LIMITED WARRANTY

TK Products, division of the Sierra Corporation, warrants that its products conform to the label descriptions, are free from manufacturing defects, and are fit for the ordinary purposes for which such goods are used. Inasmuch as the use of TK Products' product by others and other factors affecting product performance are beyond TK Products' control, TK Products does not guarantee the results to be obtained. There are no warranties except as stated herein, either express or implied, including implied warranties of merchantability or fitness for a particular purpose. SHOULD ANY TK PRODUCTS' PRODUCT FAIL TO GIVE SATISFACTORY RESULTS, TK PRODUCTS WILL REPLACE THE PRODUCT, OR AT ITS OPTION, REFUND THE PURCHASE PRICE. THIS IS THE SOLE AND EXCLUSIVE REMEDY FOR ANY FAILURE OF TK PRODUCTS' PRODUCTS TO PERFORM AS WARRANTED AND SHALL ALSO CONSTITUTE LIQUIDATED DAMAGES IN CASE OF LOSS. UNDER NO CIRCUMSTANCES SHALL THE BUYER BE ENTITLED TO ANY OTHER REMEDY OR DAMAGES. REMEDIES FOR INCIDENTAL AND CONSEQUENTIAL DAMAGES ARE SPECIFICALLY EXCLUDED. TK Products does not authorize any person to assume for it any other liability in connection with the sale or use of its products unless specifically authorized by TK Products in writing.

TK DISCLAIMER:

Every effort has been made to ensure the accuracy of the above information and to avoid infringement of any patent or copyright. The information is based on field tests by government and private agencies, as well as lab tests, and on technical data from raw material manufacturers. The person(s) specifying or requesting the use of these products is responsible for assuring their suitability for a specific use, as well as the proper application of the products. Where there is any question as to the suitability of a particular product, a small test patch is recommended. See also CONDITIONS OF SALE/ LIMITED WARRANTY (Section 7) above.

**TK Products Construction Coatings**

11400 West 47th Street Minnetonka, MN 55343

800-441-2129 toll free | 952-938-8084 fax | www.tkproducts.com